Polythene Faced Glassfibre Roll 521



Technical Data Sheet

Polythene faced glassfibre roll for thermal applications.

PRODUCT

Glassfibre insulation factory bonded to a polythene layer.

APPLICATION

Polythene Faced Glassfibre Roll (521) is used in a variety of applications and markets to support thermal performance requirements.

FEATURES and BENEFITS

- 80mm 200mm thickness
- · Black polythene faced
- Bespoke thicknesses and sizes available

PERFORMANCE

Thermal Conductivity 0.044 W/mK

SPECIFICATION

Roll Thickness (mm)	Roll Width (mm)	Roll Length (m)
80	1200	10.4
100	1200	9.17
150	1160	6.65
200	1160	4.85

STORAGE

Adequate internal storage raised off ground.

INSTALLATION

Fixing detail is dependent upon the intended application.

In most circumstances the polythene facing should be placed to the warm side of the structure as a vapour check.













IMPORTANT: Directions for use are given for guidance only and are not intended to form part of any contract. They should be varied or adapted to suit your particular materials or conditions of use. It is strongly recommended that prospective users test a sample of the product under their own conditions to satisfy themselves of its suitability for the intended purpose. For the Pre Completion Testing route to compliance with the Building Regulations Mayplas may provide site test evidence (where available) concerning the use of their product in a similar overall construction. Test evidence of a product passing minimum standards in one construction is not a warranty or specification that the same product will meet the desired acoustic performance level in any other building. Such evidence can only be considered indicative and should not be relied upon.