# Glass Cloth Faced Stone Mineral Wool Slab - MP576



Technical Data Sheet


MP576 Glass Cloth Faced Stone Mineral Wool Slab is a generic slab which can be used for a multitude of applications.

#### **PRODUCT**

MP576 consists of either a white or black cloth faced stone mineral wool slab in a range of densities, thicknesses and sizes, as per the customer's needs.

## **FEATURES and BENEFITS**

Feature	Benefit
Range of densities	Choice of thermal conductivity
Range of thickness	To suit installation requirements
Glass cloth facing	Minimises fibre shedding
White or black glass cloth	Match or contrast area of installation



## **TECHNICAL PROPERTIES**

Glass Cloth Facing	White or Black 200g/m² weavelock facing
Thickness range	25, 30, 40, 50, 60, 75, 100mm Other sizes are available as specials
Density	33, 45, 60, 80, 100, 140kg/m³
Slab Size	600mm x 1200mm
Width of cavity (for barriers)	From 25 to 100mm cavities
Thermal Conductivity (W/mK)	33kg/m³ - 0.037 W/mK 45kg/m³ - 0.035 W/mK All other densities - 0.034 W/mK
Management System	Management systems certified as meeting the requirements of ISO 9001, ISO 14001, ISO 45001
NBS	Our products can be found on NBS Source

#### **STORAGE**

Keep dry during storage and delivery.

Products should be stored away from the elements until ready for installation.







IMPORTANT: The information provided within this document is believed correct and to the best of our available knowledge as at its revision date. The information should only be used as guidance for safe handling, use, processing, storage, transportation and disposal and should not be considered as obligation in respect of warranty of (technical) performance, quality (specification) or suitability for any particular application. It is strongly recommended that prospective users test a sample of product under their own conditions to satisfy themselves of its suitability for an intended purpose and that expert advice be sought where different applications are contemplated, or where the extent of any application is in doubt. Due to our policy of continuous improvement we reserve the right to alter or amend published specification or design without prior notice. Reproduction of any part of this publication in any manner is not permitted without our prior written consent.